

GLASS SAND FINE - STJ 06

Humidity in a wet state	8,0 % max
Humidity in a dry state	0,2 % max
pH	7,3

Sieves mm	Residue		Bottom
	g	%	%
0,400	0	0	100,00
0,315	0,87	0,87	99,13
0,200	57,07	57,07	42,06
0,100	37,77	37,77	4,29
0,063	4,22	4,22	0,07
< 0,063	0,07	0,07	0,00
Total	100	100	

Fe ₂ O ₃ %	0,006
MK _{calc} Mean grain size mm	0,202
AFS	67,19
d ₅₀ mm:	0,216
d ₇₅ mm:	0,155
d ₂₅ mm:	0,266
log w	37,53
log w %	33,69
S _{th} Theoretical specific surface cm ² /g:	123,68
n _{th} Theoretical specific number of the grains pieces/g	467307

